

C-5 Corrosion Program 2011

Air Force Corrosion Conference



Dan McTish C-5 Engineering 770-494-4489 dan.j.mctish@lmco.com

maintaining the data needed, and c including suggestions for reducing	lection of information is estimated to ompleting and reviewing the collect this burden, to Washington Headqu uld be aware that notwithstanding ar DMB control number.	ion of information. Send comments arters Services, Directorate for Info	s regarding this burden estimate or properties or street	or any other aspect of the control o	his collection of information, Highway, Suite 1204, Arlington	
1. REPORT DATE AUG 2011	2. REPORT TYPE			3. DATES COVERED 00-00-2011 to 00-00-2011		
4. TITLE AND SUBTITLE				5a. CONTRACT NUMBER		
C-5 Corrosion Program 2011				5b. GRANT NUMBER		
				5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S)				5d. PROJECT NUMBER		
				5e. TASK NUMBER		
				5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Lockheed Martin Aeronautics Company, C-5 Engineering, Pinellas Park, FL, 33781				8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)		
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)		
12. DISTRIBUTION/AVAIL Approved for publ	LABILITY STATEMENT ic release; distributi	on unlimited				
	otes 11 Air Force Corro deral Rights License		ld 16-18 Aug 2011	at Robins A	.FB, GA. U.S.	
14. ABSTRACT						
15. SUBJECT TERMS						
16. SECURITY CLASSIFIC	17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON			
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified	Same as Report (SAR)	39	RESI ONSIBLE LEASON	

Report Documentation Page

Form Approved OMB No. 0704-0188



Presentation Overview



- Corrosion Program Team
 - Corrosion Control Website
 - Corrosion Program Concerns
- Non-Chrome Paint System Evaluations
- Coatings for Abrasion Protection
- Plastic Media Blasting for Paint Removal
- Material Changes to Resolve Corrosion and SCC Issues
- Aircraft Wash Procedure Development
- Av-Dec® Tape/Gasket Usage
- Lavatory Modification to Resolve Leaks
- Structural Grind-Out Limitations for Surface Corrosion
- Structural Bonding Process and Certification
- CPC Usage
- C-5M Refurbishment and Anti-Skid Removal Evaluation



C-5 Corrosion Program Team



WR-ALC Program Manager - Clay Elliott

- Operating Base Maintenance Personnel
- WR-ALC Equipment Specialist (Joel Mixon, Ron Walderman)
- WR-ALC ASIP Manager (Dave Wilkinson)
- Systems Branch Chief (Scott Wrigley)
- WR-ALC Electrical/Avionics (Jan Ewing, Nick Pitman)
- WR-ALC Depot Maintenance Personnel
- Air Force Corrosion Prevention and Control Office
 (Mac McKenna, SMSgt Scott Pagenkopf, Owen Jett)
- MSG-3 Team (Chris Carlton, Ed Reardon, Jackie Mason)
- Lockheed Martin (Dan McTish)
- Mandaree Enterprise Corporation (Mike Surratt, Larry Cornwell, Eric Lee, John Lindsey, Ed Reid, Talmadge Hutchins, Tom Helms, Josh Kingsley)



C-5 Program Implementation Team



Wing Corrosion Control Contacts

- Westover ARB (SMSgt Rob Ivey, SMSgt Mike Dirienzo, MSgt Joe Whalen)
- Stewart ANGB (SMSgt Vince Lepore, Jeff Peak)
- Lackland AFB (SMSgt Rodney Rael, MSgt Tom Bailey)
- Martinsburg ANGB (MSgt Ed Schwartz, Chuck LaFaver)
- Wright Patterson AFB (MSgt Joe Taylor)
- Memphis ANGB (CMSgt Mark Wagner, Craig Tow)
- Dover AFB (Dennis Walston, Greg Long, MSgt Reece Coleman)
- Travis AFB (MSgt Logan Commins, MSgt Sheldon Jentzsch)


WR-ALC Maintenance Contacts

- Corrosion Control Supervisor (Hector Herrera)
- Planning (Andy Ivey)
- MRRB (Jim Rivers)



Corrosion Control Website - AFIRM

https://c5.robins.af.mil/afirm/asip/corrosion/corrosion.htm





C-5 Corrosion Program Concerns



Current Base Level Concerns

- New technicians expected to have working knowledge
 - Corrosion removal and repair methods
 - Use of AMS-1640 De-Oxidation prior to Alodine application
 - Grit-Blast/Sol-gel Bonding Certification per TO 1C-5A-3
- Qualified Products Lists (QPL's) need updated
- Materials not available with improved stress corrosion ratings (7249/7050/7085) to replace 7075-T6.

Engineering Concerns

- Problem identification and resolution are quick to develop (3 months), but long to implement (+1 year)
 - Obtaining parts takes a long time (+1 year)
 - TCTO kits must be created to ensure sufficient stock is on hand



Base Level Feedback



- Continue (or increase) engineering base level visits
 - Keeps communication lines open
 - Updates engineers on base capabilities and limitations (always changing)
 - Emphasizes being proactive instead of reactive
 - Encourages base level participation in evaluating resolutions to CPAB action items
 - Always Prototype/Kit-Proof CPAB corrective actions
- Too much time and money spent on studies and tests
 - Need real time solutions with implementable corrective actions



Non-Chrome Finish Systems Beachfront/Laboratory Testing



- Tests proceeding with qualified products.
 - Testing to be done with complete coating stack-up.
 - Outdoor exposure testing with Battelle and AFRL/CTIO at Daytona and Tyndall AFB.
 - PreKote/Aerodur 2100 (Mg-Rich)/Aerodur 5000 (AkzoNobel System)

F-15

- PreKote/Aerodur 2100 (Mg-Rich)/99GY001
- RECC1015/RECC3021/02GN093/99GY001 (Deft System)
- Alodine 5200/53055GEP-17036CEH35515APX-35502CMU (Hentzen System)

C-5


- EAP-9/PRC CA7236 or CA7502/PRC CA9311 (PPG)
- PreKote/Deft 02-Y-040/Deft 99-GY-001 (Control 1)
- Alodine 1200/Deft 02-Y-040/Deft 99-GY-001 (Control 2)




Non-Chrome Finish Systems _ Flight Testing with Battelle Sensors



- Test coatings include all beachfront /lab test coatings.
- Following coating systems also in flight tests.
 - Turcoat Alumigold/Deft 44GN098(F-35)/Deft 99GY001
 - Alodine 5700/Deft 02GN084(F-22)/Deft 99GY001







Slat Lower Surface Coating and Wing Leading Edge Tape to Reduce Wear





-Desothane®HS CA8100
Anti-Chafe Topcoat
under Slat
— 8681 HS Tape with
DP190 Edge Seal on
top of wing

8681HS (Color 36173) Tape NSN 9330-01-580-6367 DP190 Edge Seal NSN 1680-01-431-3607 Slat (Extended)

C-5 Wing Leading Edge Abrasion Tape



Plastic Media Blasting (PMB) Summit held at Robins on 8-9 June 2011



- Hydrogen peroxide activated benzyl alcohol (HP/BA) chemicals are still being used at Robins/Hill/Tinker AFB
 - Chemicals being used to de-paint non-composites
 - Scuff sanding on composites
 - More time would be required for PMB
- PMB (MIL-P-85891, Type VIII media) used on B-1 at Tinker AFB
 - Type VIII is used to acquire faster strip rate over Type VII
 - Media flow rates, nozzle pressure, stand-off distances, and impingement angles continue to be refined
- PMB (MIL-P-85891, Type VIII) used on CH-47 rotor blades.
 - US Technologies provided media recovery and separation system
 - Stripping performed by US Technologies certified artisans
- Type VIII media or any other media, if used incorrectly, can be devastating and detrimental to aircraft components



Plastic Media Blasting (PMB) on C-5



- PMB (Type V media) on C-5 at Kelly AFB in 1990's
 - Approval based upon testing by SwRI
 - PMB not possible on resin-starved composites
 - Facility has been converted back to chemical stripping
- PMB (Type VIII media) being proposed for C-5 at Robins AFB
 - Need additional de-paint capability
 - Building 59D built for PMB stripping of C-5/C-17 aircraft
 - PMB (Type VIII) not currently allowed on anodized/clad, composites, aluminum substrates less than 0.032 inches, and face sheets of bonded panels less than 0.016 inches
 - Test plan submitted for evaluation of Type VIII media on surfaces outside existing limitations.
 - Residual stress, fatigue life, anodize and cadmium removal, clad erosion, crack closure, surface roughness.
 - Standard Process needs developed with aircraft mapping.
 - Training/Certification plan needs to be established.



Horizontal Stabilizer Pivot Shaft Pin 4340 replaced with Ferrium® 553









Current **Initiative** with Alcoa

7085-T7452 Die Forging per AMS4403 and 7085-T7452 hand forging per AMS4414 being Tested for Residual Stress, Crack Growth, and DTA based upon F-35 data.



7249-T73 Die Forging Selected to Replace Existing 7075-T6 Die Forging 7249-T7452 or 7050-T7452 Cold Worked, Hand Forgings as Alternate



C-5A Aft Crown Skin Replacement FS1603 to FS2273








C-5A Aft Crown Skin Replacement 7475-T761 replaced 7079-T6








C-5A Aft Crown Skin Replacement Access Doors had Steel Corner Doublers







C-5A Aft Crown Skin Replacement



Corrosion Issues:

- SCC cracks occurring in 7079-T6 skins
- Corrosion around Doors and Hatches (Galvanic)
- Corrosion found under Antenna (Av-Dec Gaskets not used)

Inspections:

- No corrosion found on faying surfaces after removal of chromated sealant (MIL-PRF-81733).
- Faying surfaces of frames and stringers looked like new.
- Fastener holes were fine with adequate edge distance and clean up possible using next oversize fastener.
- No unexpected issues.



C-5A Aft Crown Skin Replacement Corrosion Prevention Steps



Skins

- 7079-T6 (1 side Clad) replaced with thicker 7475-T761 (2 side Clad)
- Clad was sulfuric acid anodized
- Chromated primer applied to both internal and external surfaces (MIL-PRF-23377, Type I, Class C2)
- Internal primed surfaces overcoated with white polyurethane (MIL-PRF-85285, Type I, Class H)
- External primed surfaces overcoated with 99GY001 Deft APC (MIL-PRF-85285, Type IV)

Doublers

- Steel (4130) corner doublers replaced with same thickness 7475 T761 clad aluminum to eliminate galvanic corrosion
- Clad external Doublers installed around all Doors/Hatches


Antenna

Av-Dec gaskets installed under antenna



C-5A Aft Crown Skin Replacement





MIL-PRF-81733
Chromated Primer on all Faying Surfaces and Fasteners

Interior Skin Surfaces
have 1 Coat of White
Polyurethane over
Chromated Primer



Aircraft Wash Procedures T.O. 1C-5A-23-1











- Aircraft Configuration
- Covers, Tooling, Equipment List
- Masking List with Pictures
- Masking Tape (3M 8979N)
- Masking Foil (MIL-PRF-131)
- Soap Type and Dilution
- Nozzles (40 °)
- Wash Pads
- Sequencing
- Inspection
- Aircraft Restoration



Aircraft Wash Pads 6" x 12" Used on C-5 Aircraft





Cleaning efficiency for Melamine is superior to white Scotch-Brite[™] on soot.

Melamine Pads tend to Wear Out Fast if Force Used Similar to Scotchbrite Pads



Melamine Pads NSN 7920-01-526-9003




Scotch-Brite ™ Pads with Rubber Coating NSN 6850-01-496-4901



Removable Panel Installation Av-Dec® HT3000RT Tape





Modified T.O. 1C-5A-23, Para 4-4.11, and T.O. 1C-5A-3, Table 12-7



Pitot Tube/Antenna Installation Av-Dec® Gasket and Thixoflex™ Gray








New Lavatory Fluid Supply Hoses TCTO 1C-5-813









Stringer Corrosion Grind Outs and Repairs Developed




Corrosion Grind Outs Preferred over Section Removals









Cor-Ban® 35 now being applied at Depot for Corrosion Prevention


27



Fuel Tank Access Flange Corrosion Grind Out Limits Established



Complete Squeeze-Out of Sealant Required around Door Retaining Ring to Prevent Moisture Entry





Structural Bonding Process Improvements Grit-Blast Sol-Gel with Fused Primer



Grit-Blast/Sol-Gel Surface Preparation prior to Bonding required on Primary and Critical Secondary Structure at Base and Depot Level per TO 1C-5A-3

Scotch-Brite/Sol-Gel Surface
Preparation only permitted at Field
Level on Secondary Structure




Grit-Blast Process





Internal





Bonding Certification Procedure for Primary and Critical Secondary Structure

re


Specimen Fabrication




Procedure developed from ASTM D3762 to allow certification of personnel at base and depot level

Humidity Chamber Required

Wedge Insertion
Environmental Exposure
Crack Extension Measurement
Specimen Separation



Failure Mode Evaluation





CPC Applications added to Maintenance Work Cards



MSG-3 Guidelines

After initial applications, only touch-ups will be required at subsequent checks.

CPC applications will be a fluid program and will be adjusted as needed.




CPC Usage Based upon Battelle Sensor Data and Visual Inspections



Bare and CPC Coated Copper and Steel Sensors Used

Coated Steel Sensor (No Corrosion)



Bare Steel Sensor (Expired)





CPC Products Selected



Hard Film (Cor-Ban 35 Undyed)

- Used on surfaces with no corrosion after visual inspection.
- Penetrating, water-displacement capabilities along with barrier type performance with one product.
- Cure to a very firm, non-tacky, barrier type film.

Wax Film (Cor-Ban 22)


- Used on surfaces which have, or may have, corrosion and are not likely to be in contact with corrosive fluids or particles.
- Excellent exposed surface protection on high strength steel.
- Does not penetrate faying surfaces very well.
- Dirt accumulation a problem with tacky coating.

- Oil Film (LPS2 for Non-Avionics, Super Corr-A for Avionics)

- Used on surfaces which may have corrosion and are susceptible to corrosive fluids or materials. (Bilge)
- Penetrate voids, cracks, and faying surfaces to displace fluids.
- Less effective in areas of high water runoff when compared to waxy or hard film compounds.

- Paste Film (Cor-Ban 27L)

Anti-seize compound for removable fasteners.






Anti-Seize Paste Film CPC Cor-Ban 27L on Removable Fasteners



Evaluation

Incorporation



Fasteners
Installed Bare
(No CPC)


Jackpad -Bolts at FS524 and

Fasteners
Installed with
Cor-Ban 27L

FS1964

Removable Panel Fasteners

Must be Accessible and Not Locked Away in Pharmacy






C-5M Interior Refurbishment at Stewart ANGB



Lighting, Trim Panels (Gray), Anti-Skid





CESCO Aqua Miser™ Ultra Boss D-115 Anti-Skid Removal Evaluation



Anodize Surface cannot be Damaged

